

an EnPro Industries company

# **Garlock BLUE GYLON<sup>®</sup> 3504**



## MATERIAL PROPERTIES

Color:	Blue		
Composition:	PTFE with Aluminosilicate microspheres		
Fluid Services <sup>1</sup> :	Moderate concentrations of acids, some caustics, hydrocarbons, solvents,		
	hydrogen peroxide, refrigerants and cryogenics		
Temperature <sup>2</sup> , °F (°C)			
Minimum:	-450 (-268)		
Continuous Max:	+500 (+260)		
Pressure <sup>2</sup> , Maximum, psig (bar):	800 (55)		
<b>P x T (max.)</b> <sup>2</sup> , psig x °F (bar x °C)			
1/32 and 1/16":	350,000 (12,000)		
1/8":	250,000 (8,600)		
Flammability:	Will Not Burn		
Bacterial Growth:	Will Not Support		
Meets Specification:	ABS (American Bureau of Shipping), FDA (Food and Drug Administration)		
	and USP (US Pharmacopeia)		

## **TYPICAL PHYSICAL PROPERTIES**<sup>\*</sup>

	• • • • • •	-		
ASTM F36	Compressibility, %:	2	5-45	
ASTM F36	Recovery, %:	30		
ASTM F38	Creep Relaxation, %:	40.0		
ASTM F152	<b>Tensile</b> , Across Grain, psi (N/mm <sup>2</sup> ):	2000 (13.8)		
ASTM D792	Specific Gravity:	1.70		
<b>ASTM D1708</b>	Modulus @ 100% Elongation, psi (N/mm2):	1500 (10.3)		
ASTM F433	<b>Thermal Conductivity (K)</b> , W/m°K (Btu.·in./hr.·ft. <sup>2</sup> .°F):	0.14-0.24 (1.00-1.65)		
ASTM D149	Dielectric Properties, range, volts/mil.			
	Sample conditioning	<u>1/16"</u>	<u>1/8</u>	-
	3 hours at 250°F:	318	-	
	96 hours at 100% Relative Humidity	245	-	
ASTM F586	Design Factors	1/16" & Under	1/8	
	"m" factor:	3.0	2.5	
	"y" factor, psi (N/mm <sup>2</sup> ):	1650 (11.4)	3000 (2	20.7)
ROTT	Gasket Constants, 1/16":	Gb=183 a=	=0.357	Gs=4.01x10 <sup>-3</sup>
	1/8":	Gb=1008 a=	=0.221	Gs=2.23
ASTM F104	Line Call Out:	F456999A9B7E99K3M6 <sup>(3)</sup>		

#### SEALING CHARACTERISTICS<sup>\*</sup>

	ASTM F37B Fuel A	DIN 3535- 4 Gas Permeability
Gasket Load, psi (N/mm2):	1000 (7)	4640 (32)
Internal Pressure, psig (bar):	9.8 (0.7)	580 (40)
Leakage	0.12 ml/hr.	<0.015 cc/min

#### Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

\* Values do not constitute specification Limits

<sup>1</sup> See Garlock chemical resistance guide.

<sup>2</sup> Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering.

<sup>3</sup> Increase in IRM Oil #903 (fourth numeral 9 is thickness, fifth numeral 9 is weight): Thickness = 1.0% max, Weight = 2.0% max. Sixth numberal 9: % Increase in Water: Weight = 1.0% max. A9: Leakage in Fuel A (Isooctane), Pressure = 9.8psig (0.7bar), Gasket Load = 1,000psi (7.0N/mm2): Typical = 0.12ml/hr, Max = 1.0ml/hr. E99: % Increase in ASTM Fuel B: Weight: 2.0% max., Thickness: 1.0% max.